



<b>Product name</b>	:	<b>MoTip Spray Putty, beige grey</b>
<b>Article number</b>	:	<b>04062</b>
<b>Supplier / Producer</b>	:	<b>MOTIP DUPLI B.V.</b>
		<b>Wolframweg 2</b>
		<b>NL-8471 XC WOLVEGA</b>
		<b>Telephone number</b> +31 561 – 69 44 00
		<b>Telefax number</b> +31 561 – 69 44 31

---

### Product description

High quality spray putty to fill small irregularities in surfaces, treated and untreated, of wood, metal and aluminium.

### Product characteristics

Fast drying  
Excellent adhesion  
Excellent filling property and coverage  
Easy to sand, both wet and dry (from grain 400)  
Corrosion preventive

### Physical and Chemical Characteristics

Contents	:	400 ml
Base	:	Acrylic resin
Colour	:	Beige grey
VOC-content	:	Approximately 82% w/w
Solid content	:	Approximately 18% w/w
Coverage	:	1,25 to 1,75 m <sup>2</sup>
Dust dry	:	After 5 to 10 minutes
Tack free	:	After 10 to 20 minutes
Hardened/re-sprayable	:	After 2 hours
Heat resistant	:	To 110°C

### Usage

**Before use, carefully read the directions on the packaging and act accordingly.**

#### Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

#### Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the spray putty in several thin layers. Before applying the next layer, again shake the aerosol. After hardening sand, either wet or dry (grain 400). Before applying a finishing coat, apply a primer.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

**The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.**